



Exterior

**Enduradeck® Alkyd Modified Acrylic Latex
Deck, Fence & Siding Stain - Solid 478XX**

Product Description:

Enduradeck Alkyd Modified Acrylic Latex Deck, Fence & Siding Stain is a low sheen finish designed for use on decks and other exposed flat areas as well as vertical siding, fences and railings that are subjected to the rigors of drastic weather and temperature conditions, abrasion, acid rain or snow. This product is self-priming over most substrates where extractive bleeding is not a concern. This high hiding stain provides maximum protection against water, ultra violet rays and general atmospheric contamination. Enduradeck Deck, Fence & Siding Stain resists cracking, peeling and blistering and can be used on new wood, previously stained wood and properly prepared pressure treated wood. Storm Stain Enduradeck contains a unique rust inhibitor to retard nail and screw head rusting.

Recommended Use:

Sundecks, railings and posts, fences, benches, trellis, wood walkways, open porches, wood screening, patios, garden enclosures, outdoor furniture and siding.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

All surfaces must be free of loose wood fibers before any application.

Stir thoroughly before and during application to insure uniform appearance. Material should be intermixed by pouring into a large container and stirring before painting large areas, to insure color uniformity. On bare wood, thin the first coat with approximately one pint water per gallon, then apply 1 or 2 unthinned finish coats. Apply evenly with a quality nylon or synthetic brush maintaining a wet edge. Start at the end of boards and go along surfaces to a break point to avoid lapping. If spraying, back brush immediately. This product may also be applied by roller or pad applicator. Clean tools and equipment immediately with warm soapy water.

New pressure treated wood must be thoroughly scrubbed with a solution of tri-sodium phosphate and water, rinsed clean and allowed to dry completely, or allowed to weather for six months, prior to staining. Light colors may have a green cast for a few months as the preservatives leach from the wood.

Decking Stain colors vary with the different varieties of wood. Samples should be tested on the actual wood being used before large areas of wood are stained.

Architectural Specifications:

For decks and fences:

Unfinished wood -

Best application

- 1 coat of Enduradeck Alkyd Modified Acrylic Latex Deck, Fence and Siding Stain Acceptable Application

- 1 coat Enduradeck 478XX thinned 10-20% with water + 1 coat of Enduradeck 478XX unthinned

Previously stained decks and fences

- 1 or 2 coats of Enduradeck 478XX

For siding and vertical surfaces

Unfinished wood (where extractive bleeding may occur)

Best application

- 1 coat of Storm Stain Troubleshooter Oil-based Primer + 1 coat of Enduradeck 478XX Acceptable application

- (Where bleeding type wood is not a concern) 1 coat of Enduradeck 478XX thinned with 10-20% water followed by 1 coat of Enduradeck 478XX unthinned.

Previously stained wood

- 1 or 2 coats Enduradeck 478XX

Precautions:

All floor coatings are more slippery when the surface becomes wet or contaminated with debris. To help reduce the potential for slipping, coated areas must be kept dry and properly cleaned of dirt, oils, food and beverage residue, water, snow, ice and any other contaminants.

Safety Information:

Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: Alkyd Modified Acrylic

Exposure: Exterior

Specular Gloss: 8 @ 60° ± 2

Volume Solids: 39.4 % ± 2

Solids by Weight: 52.7 % ± 2

Vehicle: 73.0 % ± 2

Pigment: 27.0 % ± 2

Dry Film Thickness: 1.9 mils

Viscosity @ 77 °F: 87 KU ± 5

Maximum VOC: 100 g/liter

Flash Pt °F: Non-combustible

Thinner: Water

Clean Up: Soap & Water

Available Colors and Bases:

Pastel Medium

Deep 6 Stock Colors

Available Package Sizes:

Gallon 5 Gallon

(Weight Per Gallon: 7.8 lbs. ± .5 lb)

Drying Times:

To Touch: 1 hrs.

To Handle: 6 hrs.

To Recoat: 4 hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 325-375 s.f./gal.

Porous: 200-275 s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush -

Synthetic, Nylon or Polyester

Roller -

3/8" Nap Synthetic Fiber

Airless Spray -

.017 to .019 Tip